

UNCLASSIFIED

AD NUMBER
AD489900
NEW LIMITATION CHANGE
TO Approved for public release, distribution unlimited
FROM Distribution authorized to U.S. Gov't. agencies and their contractors; Administrative/Operational Use; Aug 1966. Other requests shall be referred to U.S. Army Missile Command, Attn: AMSMI-RR, Redstone Arsenal, AL.
AUTHORITY
USAMC ltr, 23 Aug 1971

THIS PAGE IS UNCLASSIFIED

AD489900

AD

REPORT NO. RR-TR-66-14

HOOP TENSION STRENGTH
OF COMPOSITE GRAPHITE-ALUMINUM TUBES

by
R. E. Ely

August 1966

Distribution Limited
See Notices Page



U.S. ARMY MISSILE COMMAND

Redstone Arsenal, Alabama

Best Available Copy

DISTRIBUTION LIMITATION

This document is subject to special export controls and each transmittal to foreign governments or foreign nationals may be made only with prior approval of this Command, Attn: AMSMI-RR.

DISPOSITION INSTRUCTIONS

Destroy this report when it is no longer needed. Do not return it to the originator.

DISCLAIMER

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

TRADE NAMES

Use of trade names or manufacturers in this report does not constitute an official indorsement or approval of the use of such commercial hardware or software.

24 August 1966

REPORT NO. RR-TR-66-14

**HOOP TENSION STRENGTH
OF COMPOSITE GRAPHITE-ALUMINUM TUBES**

by

R. E. Ely

DA Project No. 1C024401A330

AMC Management Structure Code No. 5025.11.29600.60

Distribution Limited

See Notices Page

**Physical Sciences Laboratory
Research and Development Directorate
U.S. Army Missile Command
Redstone Arsenal, Alabama 35809**

ABSTRACT

Composite tubes, consisting of a graphite liner confined in an aluminum sleeve, were subjected to hydrostatic burst tests at room temperature. The pressure at which the graphite liner failed is increased significantly by the reinforcing sleeve. The results are compared with a theoretical expression based on strength of material considerations.

CONTENTS

	Page
Abstract	ii
1. Introduction	1
2. Test Materials and Method	1
3. Analytical Method	2
4. Results	4
5. Conclusions	6
Literature Cited	15

ILLUSTRATIONS

Table

I	Fracture Pressures for Composite Tubes with Small Clearances	7
II	Fracture Pressures for Composite Tubes with Large Clearances	8

Figure

1	Test Specimens and Plug Fixture	9
2	Pressure-Time Record for Composite Tube Test ...	10
3	Nomenclature	11
4	Fractured Graphite Tubes	12
5	Fracture Pressure of Confined Graphite Tubes with Small Initial Clearances	13
6	Fracture Pressure of Confined Graphite Tubes with Large Initial Clearances	13
7	Stress Levels in Aluminum Sleeve at Graphite Tube Failure Pressures	14

1 Introduction

Hot-gas ducts for rocket motors normally are lined with an insulating material which may serve also as a heat sink. Graphite is a good candidate liner material which has both a low density and erosion rate. Its short-time strength at elevated temperatures, though low in magnitude, surpasses the high-temperature strength of many metals.¹

In typical applications, hot-gas ducts are subjected to high internal pressure loading which precedes extensive heating. Therefore, exploratory tests at room temperature were made to determine the fracture behavior of a graphite liner confined in a metallic sleeve. The test method employed caused the tube assembly to be subjected essentially to simple hoop tension stresses. To facilitate the analytical work, it was decided that the initial contact pressure or clearance between tubes should be zero. Since obtaining a zero clearance by mechanical means would be difficult, the tubes were machined with a known clearance and contact between the tube surfaces was accomplished by filling the annular void with an epoxy resin that was filled with metallic powder.

2 Test Materials and Method

All of the graphite tube specimens had a nominal inside diameter of 2.000 inches, an outside diameter of 2.625 inches, and a length of 8 inches (Figure 1). These specimens were machined from Graph-I-Tite, Grade G, which was received in the form of tubular stock: $1\frac{13}{16}$ -inch inside diameter, $2\frac{3}{4}$ -inch outside diameter, and 48 inches long. This graphite was fine-grained and had an apparent density of 1.88 grams/cubic centimeter. All cylindrical surfaces were paper polished after machining.

The aluminum sleeves, in which the graphite tubes were installed (Figure 1), were machined from 6061-T6 tubular stock. These sleeves were machined with wall thicknesses of 0.050, 0.075, and 0.100 inch; they also were 8 inches long and had a nominal inside diameter of 2.625 inches. To provide a known radial clearance between the graphite outside diameter and aluminum inside diameter surfaces, the aluminum sleeves were machined first and then the graphite tubes were machined and mated to a particular sleeve. Two sets of clearances were used. For tube assemblies with "small" clearances, the difference in inside diameter and outside diameter ranged from 0.002 to 0.004 inch; for the "large" clearances, this difference ranged from 0.009 to 0.012 inch.

Just before final assembly of the composite tube specimens, both the outside diameter surfaces of the graphite tubes and the inside diameter surfaces of the aluminum sleeves were coated with a thin layer of epoxy resin filled with aluminum powder. By volume, this coating consisted of 50 parts resin (EPI-REZ-510, Jones Dabney Company), 50 parts curing agent (EPI-CURE-855, Jones Dabney Company), and 100 parts aluminum powder (grade 101, Metal Disintegrating Company). The excess coating material was eliminated during assembly, which in most cases could be readily accomplished by manual means. For several of the assemblies with small clearances, however, a force of the order of 100 pounds was required to insert the graphite tube completely into the aluminum sleeve.

The composite tube specimens were potted in two batches which are referred to as Run Nos. 1 and 2. Identical procedures, which included a resin drying period of from 12 to 14 days before testing, were used in both cases.

The composite tube assembly, as well as graphite tubes individually, was subjected to internal fluid (water) pressure by using a plug fixture which utilized rubber O-rings for sealing (Figure 1). The distance between the centerlines of the O-ring grooves was $7\frac{1}{2}$ inches. In all cases, a thin coating of paraffin was applied to the graphite's inside diameter surface to prevent or minimize fluid penetration into the graphite. A simple piston and cylinder assembly driven by the crosshead motion of a universal tester was used for the pressurization source. The internal pressure history within the test specimen was sensed by a standard pressure cell and was recorded as a function of time (Figure 2); the peak pressures, also, were indicated on a bourdon tube-type gage.

Post-test inspections of the internal surfaces of the graphite tubes were made in order to reveal the failure cracks. In the inspection method, a TiO_2 developer and a red dye penetrant were utilized. These were applied after removing the paraffin coating. Pre-test inspections were performed only on the graphite specimens that were used during Run No. 2.

3. Analytical Method

The experimental fracture pressure results for the graphite tubes confined in metal sleeves were compared to predictions which were based on the strength of material consideration.

In Figure 3, Tube No. 1 corresponds to the graphite tube while Tube No. 2 refers to the metallic sleeve. The graphite tube will fracture in hoop tension at radius "a" when the internal pressure, p_i , reaches a given magnitude. Assigning the same radius, "b," to the outside diameter of Tube No. 1 and the inside diameter of Tube No. 2 implies that initially the two tubes were in contact and there were no prestresses. The contact pressure, p_0 , was generated as the composite tube assembly was expanded. Further, it must be assumed that only elastic deformations took place and that both tube materials had isotropic properties. For the metal tube, the experiment can easily be designed so that only elastic deformation would take place. For the graphite tube, the assumption of elastic behavior to fracture conditions was not true but was reasonable. The assumption of isotropic elastic properties for the graphite was invalid. In this exploratory study, therefore, it was assumed that typical or average properties, with respect to various physical directions, could be employed.

With the above assumptions, the following expression for the internal pressure at which the graphite will fail in hoop tension may be derived readily from the radial displacement equations for thick wall cylinders:²

$$p_i = \sigma_1 \frac{\alpha - \mu_1 + (\beta + \mu_2)E_1/E_2}{1 - \alpha\mu_1 + \alpha(\beta + \mu_1)E_1/E_2} \quad (1)$$

where

$$\alpha = \frac{b^2 + a^2}{b^2 - a^2} \quad (\text{See Figure 3.})$$

$$\beta = \frac{c^2 + b^2}{c^2 - b^2} \quad (\text{See Figure 3.})$$

μ_1 = Poisson's ratio for Tube No. 1

μ_2 = Poisson's ratio for Tube No. 2

E_1 = Young's modulus for Tube No. 1

E_2 = Young's modulus for Tube No. 2

σ_1 = Tensile strength of Tube No. 1

p_i = Internal pressure at fracture of Tube No. 1

Equation (1) for $\mu_2 = \mu_1$ and $E_2 = E_1$ reduces to

$$P_1 = \sigma_1 \frac{c^2 - a^2}{c^2 + a^2} \quad (2)$$

or the standard thick wall stress formula for a tube made of a single material and without a cylindrical interface.

4. Results

The internal pressures, at which the graphite tubes failed while confined in aluminum sleeves, were determined for 29 room temperature tests (Tables I and II). The time-to-fracture periods ranged from about 130 to 260 seconds; these periods were defined as the time required for the pressure to increase from 10 percent of the failure pressure to the failure pressure (Figure 2). The average (five tests) hoop tensile strength for the graphite tubes when not confined was 3157 psi which corresponds to an internal pressure of 838 psi at fracture. This tensile strength was greater than the vendor's value (2900 psi) as well as a value (2840 psi) reported for thin-wall tubes tested hydrostatically.⁵ The primary fracture mode (Figure 4) was a single longitudinal crack.

The fracture pressures for tube assemblies with small initial clearances were compared with theoretical curves in Figure 5. These curves were constructed by using Equation (1) and the following values:

$a = 2.000$ inches

$b = 2.625$ inches

$c = \text{variable}$

$E_1 = 1,500,000$ and $1,800,000$ psi

$E_2 = 10,000,000$ psi

$\mu_1 = 0.10$

$\mu_2 = 0.33$

$\sigma_1 = 3157$ psi

The elastic modulus given by the vendor for the graphite was 1.8×10^6 psi, and it was assumed to be with-the-grain. The 1.5×10^6 psi was an arbitrary value and one which probably was less than an average value for the with- and across-grain moduli. The average modulus, 1.3×10^6 psi, for ATJ graphite, for example, was only about 10 percent less than the with-grain modulus, 1.45×10^6 psi.⁴

The Poisson's ratio for the graphite, 0.10, was a typical value.⁵ To determine the significance of using this value, failure pressure calculations, also, were made when using ratios of zero and 0.2. The resulting pressure magnitudes only varied about 2 percent from the value obtained when using a ratio of 0.10.

The agreement between the results and theory was reasonable for the tube assemblies with small initial clearances (Figure 5). Several of the failure pressures exceed significantly the predicted values. This behavior might be attributed to the fact that the graphite was prestressed compressively. As indicated previously, force was required in some cases to insert the graphite tubes completely into the aluminum sleeves; volumetric shrinkage of the filled-resin while curing would have been small, say, 2 percent. The graphite tube failure modes were primarily a single crack which was readily observable; this mode also was verified by the red dye inspection method for Test No. T-1112 where the failure pressure was quite low (Table I).

The failure pressures obtained when using large initial clearances (Figure 6) in general were reduced in magnitude, and several of the values were quite low. In Table II, the three low values associated with triple cracking were not plotted in Figure 6. These data were discarded because pre-test inspections of two untested graphite tubes revealed such damage, and this damage was attributed to excessive chucking pressure with a 3-jaw chuck during machining. The other two low values, Test Nos. T-1119 and T-1127, were not discarded nor can they be explained since these graphite tubes failed with the usual, single crack.

Figure 7 shows theoretical curves for the hoop tension stress in the aluminum sleeve immediately before and after the graphite tube fails. The lower curve was constructed by calculating stress values by means of the thick-wall formula for the contact pressures predicted by Equation (1). The maximum stress developed in the aluminum sleeve immediately before the graphite fails was of the order of 12,500 psi for all wall thicknesses. After the graphite tube fails (it was assumed that only the aluminum sleeve is available for containing the fluid pressure) the aluminum would yield for wall thickness of about 0.040 inch and less.

5. Conclusions

The results indicated that it is advantageous to use the load carrying capacity of both components of a graphite-aluminum composite tube at room temperature. To insure satisfactory performance, the graphite liner should be free of flaws and contact between the liner and outer sleeve must be positive. Increases in performance could be obtained by intentionally prestressing compressively the graphite tube. Prestressing would be essential for high-temperature applications since the thermal expansion of the graphite is much less than for aluminum. Other factors to be considered would include the thermal stresses in the sleeve material and the heat sink capabilities of the complete assembly. In future studies, attention should be given to the high-temperature performance of composite tubes with controlled prestressing. The prediction theory would have to be modified to account for thermal stresses and the anisotropic properties of the liner material; the elastic constant of this material also should be evaluated thoroughly.

**Table I. Fracture Pressures for Composite Tubes
with Small Clearances**

Test No.	Aluminum Wall Thickness, mils	Pressure at Fracture, psi	Fracture Time (Estimated), sec	Run No.
T-1104	50	1880	220	1
T-1105	50	*1125	198	1
T-1106	50	1500	246	1
T-1120	50	1755	141	2
T-1121	50	1390	129	2
T-1122	50	1420	156	2
T-1111	75	2130	148	1
T-1112	75	†875	---	1
T-1123	75	1645	148	2
T-1124	75	1775	168	2
T-1125	75	2100	161	2
T-1116	100	1940	193	1
T-1117	100	2170	---	1
T-1102	100	2250	189	1

*Pre-test inspection revealed flaw on inside diameter
surface of graphite tube.

†Post-test inspection revealed single longitudinal failure
crack in graphite tube.

**Table II. Fracture Pressures for Composite Tubes
with Large Clearances**

Test No.	Aluminum Wall Thickness, mils	Pressure at Fracture, psi	Fracture Time (Estimated), sec	Run No.
T-1107	50	*610	---	1
T-1108	50	1460	242	1
T-1109	50	1660	261	1
T-1126	50	1500	---	2
T-1127	50	†860	---	2
T-1128	50	*530	---	2
T-1113	75	1610	168	1
T-1114	75	1520	174	1
T-1115	75	1880	184	1
T-1129	75	*700	---	2
T-1130	75	1800	---	2
T-1131	75	1800	---	2
T-1118	100	2050	---	1
T-1119	100	†1300	---	1
T-1103	100	1660	---	1

*Post-test inspection revealed three longitudinal cracks in graphite tube spaced at approximately 120 degrees.

†Post-test inspection revealed single longitudinal failure crack in graphite tube.




Figure 1. Test Specimens and Plug Fixture




Figure 1. Pressure-Time Record for Composite Tube Test




Figure 3. Nomenclature




Figure 4. Fractured Graphite Tubes




Figure 5. Fracture Pressure of Confined Graphite Tubes with Small Initial Clearances




Figure 6. Fracture Pressure of Confined Graphite Tubes with Large Initial Clearances




Figure 7. Stress Levels in Aluminum Sleeve at Graphite Tube Failure Pressures

LITERATURE CITED

1. Air Force Systems Command, Wright-Patterson Air Force Base, Ohio, RESEARCH AND DEVELOPMENT ON ADVANCED GRAPHITE MATERIALS, PHYSICAL PROPERTIES OF SOME NEWLY DEVELOPED GRAPHITE GRADES, VOL. XXVI by R. B. Dull, May 1964, WADD TR 61-72.
2. S. Timoshenko, STRENGTH OF MATERIALS, PART II, ADVANCED THEORY AND PROBLEMS, 3rd Edition, New York, New York, D. VanNostrand Co., Inc., 1956, p. 210.
3. R. E. Ely, STRENGTH OF GRAPHITE TUBE SPECIMENS UNDER COMBINED STRESSES, Journal of the American Ceramic Society, Vol. 48, No. 10, October 1965, pp. 505-508.
4. INDUSTRIAL GRAPHITE ENGINEERING HANDBOOK, National Carbon Co., Division of Union Carbide Corp.
5. Air Force Systems Command, Wright-Patterson Air Force Base, Ohio, RESEARCH AND DEVELOPMENT ON ADVANCED GRAPHITE MATERIALS, METHODS OF MEASURING MECHANICAL PROPERTIES OF GRAPHITE IN THE 20° TO 2700° C TEMPERATURE RANGE, VOL. XXXV by M. B. Manofsky and R. B. Dull, April 1964, WADD TR 61-72.

~~UNCLASSIFIED~~
Security Classification

DOCUMENT CONTROL DATA - R&D		
<small>(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)</small>		
1. ORIGINATING ACTIVITY (Corporate author) Physical Sciences Laboratory Research and Development Directorate U. S. Army Missile Command Redstone Arsenal, Alabama 35809		2a. REPORT SECURITY CLASSIFICATION Unclassified
3. REPORT TITLE HOOP TENSION STRENGTH OF COMPOSITE GRAPHITE-ALUMINUM TUBES		2b. GROUP
4. DESCRIPTIVE NOTES (Type of report and inclusive dates)		
5. AUTHOR(S) (Last name, first name, initial) Ely, R. E.		
6. REPORT DATE 24 August 1966	7a. TOTAL NO. OF PAGES 19	7b. NO. OF REFS 5
8a. CONTRACT OR GRANT NO.	8b. ORIGINATOR'S REPORT NUMBER(S) RR-TR-66-14	
9. PROJECT NO (DA) 1C024401A330 AMC Management Structure Code No. 5025.11.29600.60	9a. OTHER REPORT NO(S) (Any other numbers that may be assigned this report) AD _____	
10. AVAILABILITY/LIMITATION NOTES This document is subject to special export controls and each transmittal to foreign governments or foreign nationals may be made only with prior approval of this Command, Attn: AMSMI-RR.		
11. SUPPLEMENTARY NOTES	12. SPONSORING MILITARY ACTIVITY Same as No. 1	
13. ABSTRACT Composite tubes, consisting of a graphite liner confined in an aluminum sleeve, were subjected to hydrostatic burst tests at room temperature. The pressure at which the graphite liner failed is increased significantly by the reinforcing sleeve. The results are compared with a theoretical expression based on strength of material considerations.		

DD FORM 1473

~~UNCLASSIFIED~~
Security Classification

KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Hoop tension strength Graphite-aluminum Graphite tubes Aluminum sleeves Composite tubes Internal, fracture, and failure pressures						

INSTRUCTIONS

1. ORIGINATING ACTIVITY: Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (corporate author) issuing the report.

2a. REPORT SECURITY CLASSIFICATION: Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. GROUP: Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. REPORT TITLE: Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parentheses immediately following the title.

4. DESCRIPTIVE NOTES: If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. AUTHOR(S): Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. REPORT DATE: Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7a. TOTAL NUMBER OF PAGES: The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. NUMBER OF REFERENCES: Enter the total number of references cited in the report.

8a. CONTRACT OR GRANT NUMBER: If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. PROJECT NUMBER: Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. ORIGINATOR'S REPORT NUMBER(S): Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. OTHER REPORT NUMBER(S): If the report has been assigned any other report numbers (either by the originator or by the sponsor), also enter this number(s).

10. AVAILABILITY/LIMITATION NOTICES: Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. SUPPLEMENTARY NOTES: Use for additional explanatory notes.

12. SPONSORING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory sponsoring (paying for) the research and development. Include address.

13. ABSTRACT: Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. KEY WORDS: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.